Aluminium Alloy 3L63 T6 Tube



SPECIFICATIONS

Commercial 2014A

Applications:

High strength drawn tubing.

Characteristic Properties:

Heat treatable alloy. High mechanical strength slightly higher than 2011 and 2017A.

CHEMICAL COMPOSITION

BS 3L63(1971) Alloy 3L63	
Element	% Present
Copper (Cu)	3.9 - 5
Manganese (Mn)	0.4 - 1.2
Silicon (Si)	0.5 - 0.9
Magnesium (Mg)	0.2 - 0.8
Iron (Fe)	0.5 max
Nickel (Ni)	0.2 max
Zinc (Zn)	0.2 max
Titanium + Zirconium (Ti+Zr)	0.2 max
Chromium (Cr)	0.1 max
Tin (Sn)	0.05 max
Lead (Pb)	0.05 max
Aluminium (Al)	Balance

ALLOY DESIGNATIONS

Aluminium alloy 3L63 - 2014A is covered by standard BS EN 4L63 (1971)

TEMPER TYPES

The most common tempers for 3L63 - 2014A aluminium tubing is:

- T6 Solution heat treated and artificially aged
- H111 Some work hardening imparted by shaping processes but less than required for H11 temper

SUPPLIED FORMS

3L63 - 2014A aluminium is supplied as drawn tube • Tube

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.8 g/cm ³
Melting Point	640 °C
Thermal Expansion	22.8 x10 ⁻⁶ /K
Modulus of Elasticity	73 GPa
Thermal Conductivity	134-155 W/m.K

MECHANICAL PROPERTIES

BS 3L63(1971) Tube	
Property	Value
Proof Stress	370 Min MPa
Tensile Strength	450 Min MPa
Elongation A50 mm	7 Min %











CONTACT

Address: (incorporated in the USA)
Tel: +44 (0)1371 811 642
Email: info@aerometalsalliance.com

REVISION HISTORY

Datasheet Updated 07 January 2014

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.

[2 OF 2]







