

SPECIFICATIONS

Commercial	6082
------------	------

Applications:

Packaging: containers, foils, collapsible tubes, radiator tubes, wide jar closures, printing plates (offset). Strip for heat exchanger, boilermaking. Insulation foils. Kitchenware. Chemical and food industry equipment, containers. Automotive trim, light reflectors. Architecture. Vessels, piping.

Characteristic Properties:

Very good corrosion resistance. Very good weldability (lowered strength values in the zone of welding). Good machinability. Good cold formability in T4 temper after a stabilizing heat treatment. Heat treatable medium high strength construction. Alloy with a strength somewhat higher than 6061. Medium high fatigue strength. Not suitable for complex sections.

CHEMICAL COMPOSITION

BS L114(1971) Alloy L114	
Element	% Present
Silicon (Si)	0.7 - 1.3
Magnesium (Mg)	0.5 - 1.2
Manganese (Mn)	0.4 - 1
Iron (Fe)	0.5 max
Chromium (Cr)	0.25 max
Zinc (Zn)	0.2 max
Titanium (Ti)	0.2 max
Copper (Cu)	0.1 max
Nickel (Ni)	0.1 max
Tin (Sn)	0.05 max
Lead (Pb)	0.05 max
Aluminium (Al)	Balance

TEMPER TYPES

The most common temper for L114-6082 aluminium is:

- T4 - Solution heat treated and naturally aged to a substantially stable condition

SUPPLIED FORMS

L114-6082 T4 Aluminium is supplied as drawn tube

- Tube

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.71 g/cm ³
Melting Point	650 °C
Thermal Expansion	23.10 x10 ⁻⁶ /K
Thermal Conductivity	167-216 W/m.K
Modulus of Elasticity	70 GPa

MECHANICAL PROPERTIES

BS L114(1971) Tube Up to and inc. 6.00mm WT	
Property	Value
Tensile Strength	310 Min N/mm ²
Elongation A	7 Min %
0.2% Proof Stress	255 Min N/mm ²

Different values for additional sizes are shown in the specification

CONTACT

Address:	(incorporated in the USA)
Tel:	+44 (0)1371 811 642
Email:	info@aerometalsalliance.com

REVISION HISTORY

Datasheet Updated	09 January 2014
-------------------	-----------------

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.