

SPECIFICATIONS

Aerospace	QQ-A-225/9 T651
Commercial	7075

A high strength aerospace aluminium alloy offering good corrosion resistance.

CHEMICAL COMPOSITION

SAE AMS QQ-A-225/9 Alloy QQ A 225/9	
Element	% Present
Zinc (Zn)	5.1 - 6.1
Magnesium (Mg)	2.1 - 2.9
Copper (Cu)	1.2 - 2
Iron (Fe)	0.5 max
Silicon (Si)	0.4 max
Manganese (Mn)	0.3 max
Chromium (Cr)	0.18 - 0.28
Titanium (Ti)	0.2 max
Others (Total)	0.15 max
Other (Each)	0.05 max
Aluminium (Al)	Balance

TEMPER TYPES

Alloy QQ-A-225/9 is supplied in a range of tempers:

- T651 - Solution heat treated, stress relieved by stretching then artificially aged
- T7351 - Solution heat treatment then specially artificially aged for resistance to stress corrosion.

SUPPLIED FORMS

Alloy QQ-A-225/9 T6511 is supplied in bar/rod

- Bar

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.81 g/cm ³
Melting Point	635 °C
Thermal Expansion	23.5 x10 ⁻⁶ /K
Modulus of Elasticity	72 GPa
Thermal Conductivity	134-160 W/m.K
Electrical Resistivity	40 % IACS

'Typical' Physical Properties are given

MECHANICAL PROPERTIES

SAE AMS QQ-A-225/9 Bar 12.7mm to 101.6mm	
Property	Value
Proof Stress	455 Min MPa
Tensile Strength	531 Min MPa
Elongation A50 mm	7 Min %

Mechanical Properties are for T651 temper Bar in diameters 12.7mm to 101mm

CONTACT

Address: (incorporated in the USA)
Tel: +44 (0)1371 811 642
Email: info@aerometalsalliance.com

REVISION HISTORY

Datasheet Updated 14 January 2019

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.